

CODE 115M : Gravillon 10/14 MOUEN

Producteur : GKM - Carrières de Mouen
Petrographie : Grés
Elaboration : Concassé tertiaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

10 14

Norme NF P 18-545 Article 10 - EN 12620 et EN 13139

Gr A

	d/2	d	D	1.4D	2D	f	FI	LA	MBF	AS	S	WA24
	5	10	14	20	28							
Incertitude U	1	5	5	1	0	0.3	4	3	2	0.15	0.1	0.5
V.S.S.+U	6.0	25.0	100.0	100.0	100.0	1.30	24.00	28	12.00	0.350	0.500	3.0
V.S.S.	5.0	20.0	99.0	100.0	100.0	1.00	20.00	25	10.00	0.200	0.400	2.5
V.S.I.	0.0	5.0	84.0	98.0	100.0	0.00						
V.S.I.-U	0.0	0.0	79.0	97.0	100.0	0.00						
Ecart-type max	1.52	4.55	4.55									

Partie informative

Résultats de production

	du 17/01/17 au 21/06/17						du 26/05/17 au 26/05/17					
	5	10	14	20	28	f	FI	LA	MBF	AS	S	WA24
Maximum	2.2	15.2	93.5	100.0	100.0	0.86	8.59					
Xf+1.25xEcart-types	1.8	14.1	92.6	100.0	100.0	0.72						
Moyenne Xf	1.0	12.4	89.6	100.0	100.0	0.47	7.67	14	3.33	0.018	0.019	0.8
Xf-1.25xEcart-types	0.2	10.6	86.7	100.0	100.0	0.22						
Minimum	0.4	9.4	85.7	100.0	100.0	0.19	7.15					
Ecart-type	0.61	1.41	2.34	0.00	0.00	0.199	0.536					
Nombre de résultats	18	18	18	18	18	18	6	1	1	1	1	1

