

CODE 112M : Gravillon 5/22 MOUEN

Producteur : GKM - Carrières de Mouen

Petrographie : Grès feldspathique

Elaboration : Tertiaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

5.6 22.4

Norme NF P 18-545 Article 10

Gr A

	d/2	d	D/2	D	1.4D	2D	f	FI	AS	LA	MBF	S	WA24
	2.8	5.6	11.2	22.4	31.5	45							
Incertitude U	1	5	6	2	1	0	0.3	4	0.15	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	66.0	100.0	100.0	100.0	1.80	24.00	0.350	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	60.0	99.0	100.0	100.0	1.50	20.00	0.200	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	25.0	84.0	98.0	100.0	0.00						
V.S.I.-U	0.0	0.0	19.0	82.0	97.0	100.0	0.00						
Ecart-type max	1.52	4.55	10.61	4.55									

Partie informative

Résultats de production

	du 30/01/17 au 28/06/17								du 26/05/17 au 26/05/17				
	2.8	5.6	11.2	22.4	31.5	45	f	FI	AS	LA	MBF	S	WA24
Maximum	2.0	5.9	42.6	99.0	100.0	100.0	1.37	9.78					
Xf+1.25xEcart-types	1.7	4.6	38.4	98.9	100.0	100.0	1.07						
Moyenne Xf	1.0	2.7	32.2	98.7	100.0	100.0	0.66	8.70	0.018	14	3.33	0.019	0.8
Xf-1.25xEcart-types	0.4	0.8	26.0	98.4	100.0	100.0	0.24						
Minimum	0.2	0.8	25.5	98.0	100.0	100.0	0.15	7.30					
Ecart-type	0.54	1.49	4.97	0.23	0.00	0.00	0.334	0.942					
Nombre de résultats	17	17	17	17	17	17	16	5	1	1	1	1	1

